

Appl. No. 10/636,028

Amendments to the Claims

1. (Currently amended) A method of cleaning a processing chamber, comprising:

providing a processing chamber having a residue material over at least one internal chamber surface, the residue being formed over the at least one internal surface during one or more processing event conducted within the processing chamber selected from the group consisting of material deposition, etching, annealing, photolithography, ion implantation, and chemical mechanical polishing;

providing a supercritical fluid in the processing chamber; and

contacting the residue material with the supercritical fluid, the contacting removing at least some of the residue material from over the at least one internal chamber surface.
2. (Original) The method of claim 1 wherein the residue material comprises at least one member of the group consisting of, a hydrocarbon, aluminum oxide, copper, a copper-comprising material, TiN, Ta₂O₅, barium strontium titanate (BST), lead zirconate titanate (PZT), strontium bismuth titanate (SBT), NH₄Cl, TiCl₄, hafnium oxide, zirconium oxide, a platinum/rhodium alloy, ruthenium, ruthenium oxide, WN_x, W, Pt, iridium, iridium oxide, HfN, Ta, TaN, aluminum nitride and Si_xN_y.
3. (Original) The method of claim 1 wherein the residue material comprises an organic material.

Appl. No. 10/636,028

4. (Original) The method of claim 1 wherein the residue material comprises an inorganic material.
5. (Original) The method of claim 1 wherein the processing chamber is selected from the group consisting of a PVD chamber, a CVD chamber, an ALD chamber, a PECVD chamber, a pulsed-CVD chamber and a high density plasma chamber.
6. (Currently amended) The method of claim 1 wherein the at least one internal surface includes a surface comprised by a disperser, a chamber wall or a substrate holder.
7. (Original) The method of claim 1 wherein the providing the supercritical fluid comprises flowing a liquid into the processing chamber and generating the supercritical phase from the liquid within the processing chamber.
8. (Original) The method of claim 1 wherein the providing the supercritical fluid comprises flowing a gas into the chamber and generating the supercritical fluid from the gas within the processing chamber.
9. (Currently amended) The method of claim 1 wherein the providing the supercritical fluid comprises introducing the supercritical fluid into the processing deposition chamber in supercritical phase.
10. (Original) The method of claim 1 wherein the supercritical fluid comprises at least one of CO₂, C₃H₈, N₂O, C₂H₆, CH₄, H₂O, Ar and NH₃.
11. (Original) The method of claim 1 wherein the supercritical fluid contains at least one of a co-solvent and a surfactant dispersed therein.

Appl. No. 10/636,028

12. (Original) The method of claim 11 wherein the super critical fluid has a polar co-solvent dispersed therein.

13. (Original) The method of claim 1 wherein the chamber is maintained at a pressure greater than or equal to the critical pressure of the supercritical fluid throughout the cleaning.

14. (Original) The method of claim 1 wherein the chamber is maintained at a temperature greater than or equal to the critical temperature of the supercritical fluid throughout the cleaning.

15. (Original) The method of claim 1 wherein the chamber is maintained at a temperature of at least about 31°C and a pressure of at least about 72.8 atm throughout the cleaning.

16. (Currently amended) A method of removing deposited material from internal surfaces of a processing system, comprising:

providing a cleaning agent comprising carbon dioxide into at least a portion of a ~~processing~~ deposition system, the carbon dioxide comprising a phase selected from the group consisting of liquid phase and a supercritical phase;

contacting the deposited material on an internal surface of the at least a portion of the deposition ~~processing~~ system with the cleaning agent, the contacting solubilizing at least a portion of the deposited material to form a solubilized fraction; and

removing the solubilized fraction from the at least a portion of the deposition system.

Appl. No. 10/636,028

17. (Original) The method of claim 16 further comprising exposing the deposited material to a pre-treatment substance prior to the contacting, the pre-treatment substance comprising at least one of a solvent and a surfactant.

18. (Currently amended) The method of claim 16 wherein the deposition system comprises a trap and wherein the internal surface of the at least a portion of the deposition ~~processing~~ system contacted comprises an internal surface of the trap.

19. (Currently amended) The method of claim 16 wherein the deposition system comprises at least one line and wherein the internal surface comprises an internal surface of the at least one line.

20. (Currently amended) The method of claim 16 wherein the deposition system comprises a substrate holder utilized for deposition within the system, the method further comprising contacting deposited material on a surface of the substrate holder with the cleaning agent.

21. (Currently amended) The method of claim 16 wherein the deposition system comprises a disperser utilized during deposition within the deposition system, and wherein the internal surface comprises a surface of the disperser.

22. (Original) The method of claim 16 wherein the carbon dioxide is liquid phase carbon dioxide.

23. (Original) The method of claim 16 wherein the carbon dioxide is supercritical phase carbon dioxide.

Appl. No. 10/636,028

Claims 24-36 (Cancelled).